

NS-1

by Noto Gultom

Submission date: 08-May-2021 09:43AM (UTC+0700)

Submission ID: 1581067600

File name: Motlan_Jurnan_EAST.pdf (1,004.66K)

Word count: 4714

Character count: 23789



Research Article

ISSN: 2576-8484

The Effect of Post-Heating Time of ZnO Thin Film on the Efficiency of ZnO/*Hylocereus polyrhizus* DSSC

Motlan * 7 and Nurdin Siregar

Affiliation: Faculty of Mathematics and Natural Sciences, Universitas Negeri Medan, Medan, Indonesia

*Corresponding author: Motlan, Faculty of Mathematics and Natural Sciences, Universitas Negeri Medan, Medan, Indonesia, Email: motlan@unimed.ac.id

Citation: Motlan and Siregar N. The effect of post-heating time of ZnO thin film on the efficiency of ZnO/*hylocereus polyrhizus* dssc (2019) 34 weiss Appli Sci Tech 3: 70-74.

Received: Dec 09, 2019

Accepted: Dec 27, 2019

Published: Dec 31, 2019

Copyright: © 2019 Motlan, et al., This is an open-access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited.

Abstract

The efficiency of *hylocereus polyrhizus* based Dye-Sensitized Solar Cell (DSSC) has been improved by the ZnO thin-film that was used as a working electrode for DSSC. The ZnO thin-film was improved by varying the post-heating time during the annealing process which was synthesized by a sol-gel spin coating method. The preparation of dye solution was conducted by cutting the *hylocereus polyrhizus* into small pieces and put into a beaker glass. The *hylocereus polyrhizus* then was crushed with a mortar until it was soft. In order to obtain the extracted ethanol was added and leaf for 24 hours in a dark room. The extract then was filtered by using filtered paper and put into a container that wrapped an aluminum foil and kept in place to avoid the extract from sun rays. The dye sample is then UV-V is tested to find the highest absorbance value and wavelength of the sample. The extract solution was used to form the ZnO/dye solar cell where the ZnO thin film dipped into natural dyes solution with the ZnO thin film being up for 24 hours to let the dye adsorbed by the ZnO thin film. The ZnO thin film was dipped into extract *hylocereus polyrhizus* function as a working electrode and put together with a platinum counter electrode that separated by Surlyn. The pasting with Surlyn was conducted by pushing the working electrode and counter electrode and heated on a hot plate of the temperature of 70-80°C to perfectly put together. The working electrode which was put together to the platinum counter electrode was injected with liquid electrolytes through a small hole on the platinum counter electrode. Electrical testing is carried out after the DSSC has been assembled by making an electrical circuit between the DSSC with a measuring instrument. The sensor value of the *hylocereus polyrhizus* was 0.652 au, at the wavelength of 538 nm. The maximum power of the DSSC is 0.10030 w/cm² and the efficiency of 0.0274%.

49 words: Dye-sensitized solar cell, Post-heating time, ZnO thin-film, Sol-gel spin coating method, *Hylocereus polyrhizus*.

Abbreviations: DSSC-Dye-Sensitized Solar Cell, DEA-Diethanolamine, VOC-Open-Circuit Voltage, XRD-X-Ray Diffraction.

Introduction

Sunlight is one of the energy sources that have an abundant energy source; however, it has not been exploited well. The energy released by angry rays is actually only received by the surface of the earth at 69% of the total solar radiant energy [1]. The supply of solar energy from sunlight received by the earth's surface reaches 8,1024 J/year, this energy is equivalent to 4,1017 watts. The amount of energy is equivalent to Ten Thousand times the energy consumption throughout the world. In other words, by closing only 0.1% of the earth's surface with solar cell devices that 15% 10% efficiency is able to meet the energy needs of the world. Solar cells are devices that convert solar energy into electrical energy, which is directly the current and voltage produced by solar cells depending on sunlight.

Solar cells based on current technological developments and manufacturing materials can be divided into three, namely: First, solar cells made of single silicon and multi-crystalline silicon. Second, thin-film solar cells and the third organic solar cells. DSSC, the third generation of chip and reliable conversion of solar energy has gained an attraction to the development of thin-layer solar cells [2,3]. DSSC consists of several components such as oxide semiconductor, dyes, the counter electrode and electrolyte. There are several ways of improving the quality of the DSSC such as obtaining a growth window of the thin film semiconductor, the molecular structure of the dyes, electrolyte

pair of reduction-oxidation and electrode material. In the engineering of the semiconductor that is used as working electrode in the DSSC, the use of ZnO thin film has given high promise due to its higher bandgap compared to TiO₂ that previously used, therefore gives higher voltage, higher carrier mobility that can reduce carrier recombination, and has structure and morphology that can be controlled in its synthesis. In addition, ZnO also has a wide bandgap of 3.37 eV, has high optical transparency at room temperature and 60 meV electron binding ability [4,5]. ZnO thin film has been synthesized by several methods such as molecular beam epitaxy, RF magnetron sputtering, pulsed laser deposition, spray pyrolysis, chemical bath deposition, physical vapor deposition [6-14].

However, this method involves a rather complicated procedure because it requires sophisticated equipment, instead of using the sol-gel spin coating method because the equipment is simple and low cost, does not use space with high vacuum and very good microstructure. Research on DSSC has been carried out using various types of semiconductors with variations in heating temperature, heating holding time, spin-coating speed and various types of dyes using thin-film TiO₂ with calcination temperature of 450°C and holding time 120 minutes and using dye extract from spinach leaves, DSSC efficiency was obtained 0.13% [15].

Citation: Motlan and Siregar N. The effect of post-heating time of ZnO thin film on the efficiency of ZnO/*hylocereus polyrhizus* dssc (2019) Edelweiss Appli Sci Tech 3: 70-74.



Thin-film TiO₂ with calcination temperature of 450°C and dye extract from Male Flower Leaves (*Luffa Cylindra-L*) obtained efficiency DSSC 1.3% [16]. Thin-film TiO₂ and dye extracts from various fruits and leaves, the result is that the magnitude of DSSC efficiency depends on the fruit or leaf extract used [17,18]. TiO₂ thin films and the variation of solvents in dye extracts from *Melastoma Malabathricum* Leaves fruit results that the magnitude of DSSC efficiency was influenced by solvents [19]. Varying the thickness of TiO₂ thin films the result is that the magnitude of DSSC efficiency is influenced by the thin film thickness [20]. Variations in the temperature of ZnO thin films (300 °C, 350 °C, 400 °C and 500 °C), the result is the highest DSSC efficiency of 3.92% at 400°C [21].

It cause ZnO has demonstrated multifunctional properties with high energy binding strength, low resistivity, great light catching characteristics, high optical transparency at room temperature, 3.37 eV wide bandgap, and the ability to bind free electrons at 60 meV. The quality of the thin film is a crucial point in the improvement of the efficiency of the DSSC. In this work, we tried to improve the quality of the ZnO thin film by varying the Post-Heating time of the ZnO thin film during the sol-gel spin coating. The aim of this research is seeing the effect of Post-Heating time of ZnO thin film on ZnO/dye-based DSSC efficiency.

Experiment Method

ZnO Thin Film Synthesis

Materials used in this research were Zinc Acetate Dehydrate, Isopropanol and Diethanolamine which successively used as basic materials, solutions, and stabilizers. The ZnO thin film was synthesized by using sol-gel spin coating method. Zinc Acetate dehydrates (Zn(CH₃COOH)₂H₂O) was diluted in isopropanol, stirred with a magnetic stirrer for 10 minutes, then little by little 1.72 ml Diethanolamine (DEA) was dropped into the solution. The solution which was in the form of the gel was dropped on an FTO glass substrate and spin with a speed of 5000 rpm. The sample then was heated with pre-heating 250°C and Post-Heating 500°C with heating with a variation of 30, 60, 90, 120 and 150 minutes. The ZnO thin film samples were then characterized by (X-Ray Diffraction) XRD, SEM, and UV-Vis.

The Preparation of Dye Solution (Sensitizer)

The preparation of dye solution was conducted by cutting the *hylocereus polyrhizus* into small pieces and put into a beaker glass. The *hylocereus polyrhizus* then was crushed with a mortar until soft. In order to obtain the extracted ethanol was added and leaf for 24 hours in a dark room. The extract then was filtered by using filtered paper and put into a container that wrapped an aluminum foil and kept in place to avoid the extract from sun rays. The dye sample is then UV-Vis tested to find the highest absorbance value and wavelength of the sample.

DSSC Synthesis

The extract solution was used to form the ZnO/dye solar cell where the ZnO thin film dipped into natural dyes solution with the ZnO thin films facing up for 24 hours to let the dye adsorbed by the ZnO thin film. The ZnO thin film was dipped into extract *hylocereus polyrhizus* function as a working electrode and put together with a platinum counter electrode that separated Surlyn. The pasting with Surlyn was conducted by pushing the working electrode and counter electrode and heated on a hot plate of the temperature of 70-80°C to perfectly put together. The working electrode which was put together to the platinum counter electrode was injected with liquid electrolytes through a small hole on the platinum counter electrode.

Efficiency Measurement

Electrical testing is carried out after the DSSC has been assembled by making an electrical circuit between the DSSC with a measuring

instrument, namely a digital multimeter as shown in Figure 1. This test is based on the lighting method of the light beam to determine the performance and efficiency of the cells obtained when the solar cell object is exposed to light with certain intensity at the top of the electrode (anode). DSSC outputs are an Open-Circuit Volt (V_{oc}) and Short Circuit Current (I_{sc}) DSSC. Then the amount of fill factor (FF) and DSSC efficiency are calculated (η).



Figure 1: DSSC Efficiency Measurement.

Result and Discussion

The crystal structure was determined by using XRD. Figure 2 shows the XRD pattern of the ZnO thin film of a sample with pre-heating 250°C and Post-Heating 500°C with the variation of 30, 60, 90, 120 and 150 minutes.




Figure 2: X-ray diffraction spectra of ZnO.

The X-ray diffraction pattern of the sample is analyzed using search march by showing the sample has the same crystal planes namely fields (100), (002), (101) and has the same growth peak and oriented to the plane (101). Analysis of the XRD pattern shows that samples are hexagonal wurtzite and growth orientation toward the C axis perpendicular to the substrate surface along with standard data of ZnO of JCPDS 80-0075 card. The ZnO crystal size measured using Scherrer equation 1 [22].

$$D = \frac{0.9 \lambda}{\beta \cos \theta} \quad (1)$$

Whereas D=crystal size, λ =wavelength, β =FWHM (Full Width Half Maximum), θ =diffraction angle.

48

Crystal sizes of the ZnO thin films calculated using equation 1 are shown in Table 1.



Post-Heating Time (minutes)	Phase	Peak		Crystal size (nm)
		2θ (degree)	FWHM (degree)	
30	ZnO	36.9775	0.375	22
60	ZnO	36.9513	0.3049	27
90	ZnO	36.9582	0.3264	27
120	ZnO	36.9545	0.3376	25
150	ZnO	36.9428	0.339	25

Table 1: Crystal size of ZnO.


The size of the crystal is influenced by the value of FWHM, if the FWHM value decreases the size of the crystal is large and vice versa. The size of the crystals obtained for all samples is almost the same in the range of 22-27 nm. This shows that the duration of heating does not affect the size of the crystal, because the difference in the duration of heating is very small. The increase in Post-Heating temperature is in line with the decreasing FWHM value and increasing crystal size, this is due to the higher heating temperature in the growth of ZnO thin film crystals, the energy obtained by ZnO atoms to form the higher the crystal field as well, so the better the Crystal formed [19-23].

14

The Optical Property of the ZnO Thin Film

Transmittance and absorption spectra for all samples were taken in the wavelength range of 300-800 nm which is in the range of its application for solar cells. Figure 3a shows there is a sharp increase in transmission of the ZO thin film in the wavelength range of 350-430 nm which is in the ultraviolet range. The highest and lowest transmission value is when the Post-Heating of 30 and 120 minutes. According to the heating mechanism the higher the heating temperature and the longer the Post-Heating time the better is the compacting of the powder and the stronger the bond among granules and porosity of the material.

The high transmission value of ZnO thin film, make it a good application for solar cell [24]. Absorbance spectrum on the ZO thin film is shown in Figure 3b. There is a sharp decrease in the adsorption for all samples in the wavelength range of 350-430 nm and the highest and lowest adsorption consecutively when Post-Heating 120 and 30 minutes. Therefore, the ZnO thin film has high transmittance at visible light and can be applied in optoelectronics. The ZnO thin film has a direct bandgap, therefore the bandgap can be calculated by using the following equation 2 [25-26].

Figure 3: Optical properties of ZnO thin film: (a) transmittance; (b) absorbance. $\frac{1}{2}(\alpha h\nu)^2 = C_D(h\nu - E_{opt})^2$

The bandgap with variations in the variation of heating to Post-Heating of various Post-Heating time of ZnO thin film which was derived using the Tauc Plot method is shown in Figure 4.





Figure 4: The bandgap of ZnO using Tauc Plot method.

40

The bandgap of Figure 4 of ZnO thin film as a function of Post-Heating. Figure 4 shows that the highest bandgap is 3.140 eV and the lowest is 3.073 eV of Post-Heating time of each 120 and 150 minutes. Generally, the bandgap increases as the Post-Heating time increase up to 120 minutes, beyond that temperature the band gap decreases. The increase in bandgap along with the increase in Post-Heating time is due to the compacting of the granules, and the decrease of porosity size and number [27-29]. The increase in density of the smaller granules will increase the surface energy as well as the bandgap. However, by further increasing the Post-Heating time will start forming bigger granules and reduce the energy gap [30].

The Absorbance of *Hylocereus polyrhizus* Dye Solution

The absorption of the sensitizer extracted red dragon dye solution which was determined by UV-Vis is shown in Figure 5.

Figure 5: Graph of wavelength Vs absorption of extracted *hylocereus polyrhizus* dye solution.

31

The absorption intensity of the *hylocereus polyrhizus* dye solution as shown in Figure 5 is 0.652 a.u. at the wavelength of 535 nm. Previous work showed that the peak absorption of the *hylocereus polyrhizus* was in the range of 420-580 and absorption intensity was affected by solution concentration, the higher the solution concentration the higher is the solution absorption value [31,32]. Absorption peaks in the range of the wavelength of 500-600 nm show that there is the content of anthocyanin in the dye solution [33-35]. The peak absorption of *hylocereus polyrhizus* at a wavelength of 535 nm which is in the range of 450-600 nm [36]. The photon absorption by the solar cell is very crucial in solar cell technology, the higher the absorption the bigger the photon excitation the bigger is the amount of solar energy converted into electricity.

The efficiency of DSSC

The percentage of efficiency is obtained by comparing the power produced by the DSSC (Pmax) prototype with the power which is given by solar (Pin) shown by the following equation 3 and the output power can be obtained from the following equation 4.

2

17

Citation: Motlan and Siregar N. The effect of post-heating time of ZnO thin film on the efficiency of ZnO/*hylocereus polyrhizus* dssc (2019) Edelweiss Appli Sci Tech 3: 70-74.



$$\eta (\%) = ((J_{SC} \times (V_{OC} \times FF \times 100)) / P_{in}) \quad (3)$$

$$P_{max} = V_{max} \times J_{max} \quad (4)$$

Table 2 Shows the efficiency ZnO/DSSC of the *hylocereus polyrhizus* based on a variation of Post-Heating time during the synthesis of ZnO thin film is shown in Table 2.

Post-Heating Time Minutes	V _{max} (V)	J _{max} (mA/cm ²)	P _{max} (W/cm ²)	P _{in} (W/cm ²)	FF (%)	η (%)
30	0.4	0.00258	0.00205	36.5	198.54	0.0056
60	0.4	0.0352	0.0015	36.5	10.638	0.0041
90	0.4	0.0075	0.00275	36.5	91.667	0.0075
120	0.4	0.013	0.1003	36.5	192.78	0.0274
150	0.4	0.0025	0.00533	36.5	532.5	0.015

Table 2: The values of voltage, current density, and DSSC efficiency with Post-Heating time variation and *hylocereus polyrhizus* dye.

22

Table 2 shows that the highest efficiency of the DSSC is when the Post-Heating time of the ZnO is 120 minutes which 0.0274%. The increase in the bandgap, as well as the increase in energy efficiency, is due to the improvement in crystal growth during the Post-Heating time. The increase in the formation of small granules, and at the same time decrease the porosity has improved the quality of the DSSC. The increase in the number of granules will facilitate electrons flow from conduction band into valence band that facilitates photocatalyst reaction and bigger absorption by the dye, and therefore bigger spectrum. Semiconductor with a wide bandgap will multiply electrons flowing from the conduction band to the valence band, which makes the photocatalyst reaction chamber and absorption by the dye will become more so that the spectrum becomes wide [37].

Conclusion

5

Dye-Sensitized Solar Cell can be fabricated by using ZnO thin film with the variation of Post-Heating time and extracted dye from *hylocereus polyrhizus*. The smallest size of the ZnO thin-film was 22 nm for Post-Heating of 30 minutes and the bandgap 3.140 eV for the Post-Heating time of 120 minutes. The intensity of extracted dye from the *hylocereus polyrhizus* Sensitizer is 0.652 a.u and peak position at 333 nm. The ZnO thin-film and *hylocereus polyrhizus* based DSSC can convert solar energy into electrical energy. The maximum power obtained in this research was 0.10030 W/cm² and the maximum efficiency of 0.0274% for the Post-Heating time during synthesis ZnO thin-film of 120 minutes.

References

- Girard EJ. Principles of Environmental Chemistry. (2nd Edn) (2010) Massachusetts: Jones and Bartlett Publishers. Massachusetts, USA.
- Grätzel C and Zakeeruddin SM. Recent trends in mesoscopic solar cells based on molecular and nanopigment light harvesters (2013) Materials Today 16: 11-18. <https://doi.org/10.1016/j.mattod.2013.01.020>
- Wang M, Grätzel C, Zakeeruddin SM and Grätzel M. Recent developments in redox electrolytes for dye-sensitized solar cells (2012) Energy and Environmental Sci <https://doi.org/10.1039/c2ee23081j>
- Ernawita E, Irwansyah I, Sawitri D and Wahyuno RA, Preparasi dan Karakterisasi Dye-sensitized Solar Cell (DSSC) dengan Pewarna Ekstrak Jeruk: Pengaruh Variasi Komposisi Karotenoid dan Flavonoid Terhadap Efisiensi Sel Surya (2017) J. Fis. dan Apl. 13: 3. <https://doi.org/10.12962/j24604682.v13i3.2839>
- Siregar N and Motlan. The Effect of Pre-heating Temperature on Structural and Optical Properties ZnO Thin Film Synthesized using Sol-Gel spin Coating Method (2018) Journal of Physics: Conference Series 1120. <https://doi.org/10.1088/1742-6596/1120/1/012088>
- Wang C, Chen Z, Hu H and Zhang D. Effect of the oxygen pressure on the microstructure and optical properties of ZnO films prepared by laser molecular beam epitaxy (2009) Phys. B Condens. Matter 404: 4075-4082. <https://doi.org/10.1016/j.physb.2009.07.165>
- Kumar Y, Escoria GJ, Singh F, Olive-Méndez SF, et al. Influence of mesoporous substrate morphology on the structural, optical and electrical properties of RF sputtered ZnO layer deposited over porous silicon nanostructure (2012) Appl. Surf. Sci 258: 2283-2288. <https://doi.org/10.1016/j.apsusc.2011.09.131>
- Zhu BL, Zhao X, Su F, Li GH, et al. Low temperature annealing effects on the structure and optical properties of ZnO films grown by pulsed laser deposition (2010) Vacuum 84: 1280-1286.
- Terasako T, Uno Y, Inoue S, Kariya T and Shirakata S. Structural, optical and electrical properties of CuInS₂ thin films prepared by chemical spray pyrolysis (2006) Physica Status Solidi (C) Current Topics in Solid State Physics 3: 2588-2591. <https://doi.org/10.1002/pssc.200669597>
- Falcade T, Oliveira DBG, Bergmann CP, Müller IL and Fraga DMC. The effects of spray pyrolysis parameters on the morphology and microstructure of the YSZ film deposited on LSM cathode (2010) 65th ABM International Congress, 18th IFHTSE Congress and 1st TMS/ABM International Materials Congress 727: 691-696. <https://doi.org/10.4028/www.scientific.net/msf.727-728.691>
- Cubillos GI, Olaya JJ, Bethencourt M, Cifredo G and Blanco G. Structural changes in ZrO_xNy/ZrO₂ coatings deposited through spray pyrolysis-nitridding (2014) Rev Mex Fis 60: 233-242.
- Kumar PS, Raj AD, Mangalaraj D and Nataraj D. Growth and characterization of ZnO nanostructured thin films by a two-step chemical method (2008) Appl Surf Sci 255: 2382-2387. <https://doi.org/10.1016/j.apsusc.2008.07.136>
- Mane RS, Lee WJ, Pathan HM and Han SH. Nanocrystalline TiO₂/ZnO thin films: Fabrication and application to dye-sensitized solar cells (2005) J Phys Chem B 109: 24254-24259. <https://doi.org/10.1021/jp0531560>
- George A, Kumari P, Soin N, Roy SS and McLaughlin JA. Structure and field emission characteristics of ZnO nanoneedles grown by physical vapor deposition (2010) Mater Chem Phys 123: 634-638. <https://doi.org/10.1016/j.matchemphys.2010.05.029>
- Chang H, Wu HM, Chen TL, Huang KD, Jwo CS, et al. Dye-sensitized solar cell using natural dyes extracted from spinach and ipomoea (2010) J Alloys Compd 495: 606-610. <https://doi.org/10.1016/j.jallcom.2009.10.057>
- Maurya IC, Srivastava P and Bahadur L. Dye-sensitized solar cell using extract from petals of male flowers Luffa cylindrica L. as a natural sensitizer (2016) Opt Mater (Amst) 52: 150-156. <https://doi.org/10.1016/j.optmat.2015.12.016>
- R. Ramamoorthy, N Radha, G Maheswari, S Anandan, S Manoharan, et al. Betalain and anthocyanin dye-sensitized solar cells (2016) J Appl Electrochem 46: 929-941. <https://doi.org/10.1007/s10800-016-0974-9>
- Lim A, Kumar NTRN, Ling TA, HuqMirza A, Chandrakanthi RLN, et al. Potential natural sensitizers extracted from the skin of Canarium odontophyllum fruits for dye-sensitized solar cells (2015) Spectrochim. Acta-Part A Mol Biomol Spectrosc 138: 596-602. <https://doi.org/10.1016/j.saa.2014.11.102>
- Singh LK, Karlo T and Pandey A. Performance of fruit extract of *Melastoma Malabathricum* L. as sensitizer in DSSCs (2014) Spectrochim. Acta-Part A Mol Biomol Spectrosc 118: 938-943. <https://doi.org/10.1016/j.saa.2013.09.075>
- Kao MC, Chen HZ, Young SL, Kung CY and Lin CC. The effects of the thickness of TiO₂ films on the performance of dye-sensitized solar cells (2009) Thin Solid Films 517: 5096-5099. <https://doi.org/10.1016/j.tsf.2009.03.102>

Citation: Motlan and Siregar N. The effect of post-heating time of ZnO thin film on the efficiency of ZnO/*hylocereus polyrhizus* dssc (2019) Edelweiss Appli Sci Tech 3: 70-74.



21. Lu L, Li R, Fan K and Peng T. Effects of annealing conditions on the photoelectrochemical properties of dye-sensitized solar cells made with ZnO nanoparticles (2010) Sol. Energy 84: 844-853. <https://doi.org/10.1016/j.solener.2010.02.010>
22. Cullity DB and Stock RS. Elements of x-ray diffraction (3rd Edn) (2014) Pearson Education India, India.
23. HA Dehkordi, K Dastafkan, A Moshaii and A Mokhtari. Thermal 30°-annealing and gas concentration effect on liquid petroleum gas sensing characteristics of nanocrystalline zinc oxide thin films (2015) J Mater Sci Mater Electron 26: 3134-3142. <https://doi.org/10.1007/s10854-015-2808-7>
24. Sathya M, Claude A, Govindasamy P, Sudha K and Claude A. Growth of pure and doped ZnO thin films for solar cell applications (2012) Pelagia Res Libr Adv Appl Sci Res 3: 2591-2598.
25. Lee JC, Kang KH, Kim SK, Yoon KH, Park II, et al. RF sputter deposition of the high-quality intrinsic and n-type ZnO window layers for Cu(In,Ga)Se₂-based solar cell applications (2000) Sol Energy Mater Sol Cells. 64: 185-195. [https://doi.org/10.1016/s0927-0248\(00\)00069-6](https://doi.org/10.1016/s0927-0248(00)00069-6)
26. Sridev D and Rajendran KV. Synthesis and optical characteristics of ZnO nanocrystals (2009) Bull Mater Sci 32: 165-168.
27. Das MD, Bhattacharya A and Shah BR. Effect of Annealing on Optical Properties of Zinc Oxide Thin Films Prepared by Homemade Spin Coater (2015) Nepal J Sci Technol 15: 111-116. <https://doi.org/10.3126/njst.v1i512.12126>
28. Yadav AB, Pandey A and Jit S. Effects of annealing temperature on the structural, optical, and electrical properties of ZnO thin films grown on n-Si ⟨100⟩ substrates by the sol-gel spin coating method (2014) Acta Metall Sin (English Letters) 27:682-688. <https://doi.org/10.1007/s40195-014-0097-4>
29. Kumar S, Basu S, Rana B, Barman A, Chatterjee S, et al. Structural, optical and magnetic properties of sol-gel derived ZnO:Co diluted magnetic semiconductor nanocrystals: An EXAFS study (2014) J Mater Chem C 2:481-495. <https://doi.org/10.1039/c3tc31834f>
30. Motlan and Goldys EM. Photoluminescence of multilayer GaSb/GaAs self-assembled quantum dots grown by metalorganic chemical vapor deposition at atmospheric pressure (2001) Appl Phys Lett 79: 2976. <https://doi.org/10.1063/1.1415351>
31. Naderi N, Ghazali HM, Hussin ASM, Amid M and Mohd MY. Characterization and quantification of dragon fruit (*Hylocereus polyrhizus*) betacyanin pigments extracted by two procedures (2012) Pertanika J Trop Agric Sci 35: 33-40.
32. Gomesh N, Syafinaz R, Irwanto M, Irwan YM, Fareq M, et al. Characteristics of Dye-Sensitized Solar Cells Using Dye from Pitaya Fruit (2015) Appl Mech Mater 793: 450-454. <https://doi.org/10.4028/www.scientific.net/amm.793.450>
33. Lai WH, Su YH, Teoh LG and Hon MH. Commercial and natural dyes as photosensitizers for a water-based dye-sensitized solar cell loaded with gold nanoparticles (2008) J Photochem Photobiol A Chem 195: 307-313. <https://doi.org/10.1016/j.jphotochem.2007.10.018>
34. Hemalatha KV, Karthick SN, Justin Raj C, Hong NY, Kim SK, et al. Performance of Kerria japonica and Rosa chinensis flower dyes as sensitizers for dye-sensitized solar cells (2012) Spectrochim Acta-Part A Mol Biomol Spectrosc 96: 305-309. <https://doi.org/10.1016/j.saa.2012.05.027>
35. Yusoff A, Kumara NTRN, Lim A, Ekanayake P and Tennakoon KU. Impacts of temperature on the stability of tropical plant pigments as sensitizers for dye sensitized solar cells (2014) J Biophys 2014: 739514. <https://doi.org/10.1155/2014/739514>
36. Ali R and Nayak N. Fabrication and analysis of dye-sensitized solar cell using natural dye extracted from dragon fruit (2010) Int J Integrated Eng 2: 55-62.
37. Motlan and Siregar N. The Effect of Post-Heating Temperature on the Efficiency of Dye Sensitized Solar Cell (DSSC) with Using ZnO Thin Film and Dye from Dutch Eggplant Fruit (*Solanum betaceum*) (2018) J Physics Conference Series 1120. <https://doi.org/10.1088/1742-6596/1120/1/012082>

Citation: Motlan and Siregar N. The effect of post-heating time of ZnO thin film on the efficiency of ZnO/*hylocereus polyrhizus* dssc (2019) Edelweiss Appli Sci Tech 3: 70-74.

PRIMARY SOURCES

- | | | |
|---|--|-----|
| 1 | www.omicsonline.org
Internet Source | 1 % |
| 2 | Ala Eddinne Touihri, Tarek Azizi, Rached Gharbi. " Transient current effect on the dye sensitized solar cells – characterization ", IET Science, Measurement & Technology, 2020
Publication | 1 % |
| 3 | Submitted to Universiti Malaysia Perlis
Student Paper | 1 % |
| 4 | www.teachinsacramento.com
Internet Source | 1 % |
| 5 | link.springer.com
Internet Source | 1 % |
| 6 | www.science.gov
Internet Source | 1 % |
| 7 | Rajagukguk, J., J. Kaewkhao, M. Djamal, R. Hidayat, Suprijadi, and Y. Ruangtawee. "Structural and optical characteristics of Eu ³⁺ ions in sodium-lead-zinc-lithium-borate glass system", Journal of Molecular Structure, 2016. | 1 % |

- 8 Submitted to Universitas Diponegoro 1 %
Student Paper
-
- 9 www.irjet.net 1 %
Internet Source
-
- 10 Deepesh Bhardwaj, Dixit Prasher, Anuj Dubey, 1 %
Vishal Dhiman, Radha Tomar. "One step
sonochemical synthesis of single phase Sr-
doped ZnO₂ nanorods", SN Applied Sciences,
2021
Publication
-
- 11 Submitted to Universiti Teknologi MARA 1 %
Student Paper
-
- 12 "Dye-Sensitized Solar Cells", Electrochemical 1 %
Energy Storage and Conversion, 2015.
Publication
-
- 13 Kim, J.. "Thiophene-fused coplanar sensitizer 1 %
for dye-sensitized solar cells", Tetrahedron
Letters, 20110525
Publication
-
- 14 Kang, S.J.. "Influence of substrate 1 %
temperature on the optical and piezoelectric
properties of ZnO thin films deposited by rf
magnetron sputtering", Applied Surface
Science, 20070630
Publication
-

- | | | |
|----|---|------|
| 15 | mafiadoc.com
Internet Source | <1 % |
| 16 | Submitted to Higher Education Commission
Pakistan
Student Paper | <1 % |
| 17 | "Nanotechnology for Energy and Environmental Engineering", Springer Science and Business Media LLC, 2020
Publication | <1 % |
| 18 | Marianna Kemell, Mikko Ritala, Markku Leskelä. " Thin Film Deposition Methods for CuInSe Solar Cells ", Critical Reviews in Solid State and Materials Sciences, 2005
Publication | <1 % |
| 19 | Motonari Adachi, Masaru Sakamoto, Jinting Jiu, Yukio Ogata, Seiji Isoda. "Determination of Parameters of Electron Transport in Dye-Sensitized Solar Cells Using Electrochemical Impedance Spectroscopy", The Journal of Physical Chemistry B, 2006
Publication | <1 % |
| 20 | www.scientific.net
Internet Source | <1 % |
| 21 | Mali, S.S.. "Synthesis and characterization of Cu ₂ ZnSnS ₄ thin films by SILAR method", Journal of Physics and Chemistry of Solids, 201206 | <1 % |

- 22 worldwidescience.org <1 %
Internet Source
-
- 23 bictel.ulg.ac.be <1 %
Internet Source
-
- 24 m.scirp.org <1 %
Internet Source
-
- 25 "Advanced Processing and Manufacturing Technologies for Nanostructured and Multifunctional Materials", Wiley, 2014 <1 %
Publication
-
- 26 Arnold Edward, Tresna Dewi, Rusdianasari. "The effectiveness of Solar Tracker Use on Solar Panels to The Output of The Generated Electricity Power", IOP Conference Series: Earth and Environmental Science, 2019 <1 %
Publication
-
- 27 Shelke, R. S., S. B. Thombre, and S. R. Patrikar. "Cobalt Sulphate as an Alternative Counter Electrode Material in Dye Sensitized Solar Cells", Journal of Solar Energy Engineering, 2014. <1 %
Publication
-
- 28 core.ac.uk <1 %
Internet Source
-
- 29 pt.scribd.com <1 %
Internet Source

<1 %

30 repository.usu.ac.id <1 %
Internet Source

31 www.hindawi.com <1 %
Internet Source

32 www.jmst.org <1 %
Internet Source

33 Abhinav Bhatnagar, Vijay Janyani. "Efficiency Enhancement In Thin Film ITO-cSi Heterojunction Solar Cell Using Photonic Crystal", 2017 14th IEEE India Council International Conference (INDICON), 2017 <1 %
Publication

34 Jong Eun Lee, Yun-Hyeon Kim, Hyo Hyun Shin, Won Gi Jeong, Kook Ju Na. "The Diagnostic Utility of Prone Position Chest CT for the Evaluation of Esophageal Cancer", Chonnam Medical Journal, 2020 <1 %
Publication

35 Kai Foo, Uda Hashim, Kashif Muhammad, Chun Voon. "Sol-gel synthesized zinc oxide nanorods and their structural and optical investigation for optoelectronic application", Springer Nature, 2014 <1 %
Internet Source

- 36 N J Egwunyenga, L N Ezenwaka, I A Ezenwa, N L Okoli. "Effect of annealing temperature on the optical properties of electrodeposited ZnO/MgO superlattice", Materials Research Express, 2019 <1 %
Publication
-
- 37 Wai Kian Tan, Zainovia Lockman, Khairunisak Abdul Razak, Go Kawamura, Hiroyuki Muto, Atsunori Matsuda. "Enhanced dye-sensitized solar cells performance of ZnO nanorod arrays grown by low-temperature hydrothermal reaction", International Journal of Energy Research, 2013 <1 %
Publication
-
- 38 Yidong Zhang, Wenjun Fa, Fengling Yang, Zhi Zheng, Pingyu Zhang. "Effect of annealing temperature on the structural and optical properties of ZnO thin films prepared by sol-gel method", Ionics, 2010 <1 %
Publication
-
- 39 cronfa.swan.ac.uk <1 %
Internet Source
-
- 40 earsiv.etu.edu.tr <1 %
Internet Source
-
- 41 eprints.kfupm.edu.sa <1 %
Internet Source
-
- iopscience.iop.org

42

<1 %

43

res.mdpi.com

<1 %

44

Alexandria R. C. Bredar, Amanda L. Chown,
Andricus R. Burton, Byron H. Farnum.

<1 %

"Electrochemical Impedance Spectroscopy of
Metal Oxide Electrodes for Energy
Applications", ACS Applied Energy Materials,
2020

45

Seong Jun Kang, Yang Hee Joung, Dong Hoon
Chang, Kyoung Won Kim. "Piezoelectric and
optical properties of ZnO thin films deposited
using various O₂/(Ar+O₂) gas ratios", Journal
of Materials Science: Materials in Electronics,
2007

<1 %

46

Xianliang Sheng. "Enhanced
photoelectrochemical performance of ZnO
photoanode with scattering hollow cavities",
Applied Physics A, 05/16/2009

<1 %

47

"Rational Design of Solar Cells for Efficient
Solar Energy Conversion", Wiley, 2018

<1 %

48

Sharul Ashikin Kamaruddin, Kah-Yoong Chan,
Ho-Kwang Yow, Mohd Zainizan Sahdan,
Hashim Saim, Dietmar Knipp. "Zinc oxide films
prepared by sol-gel spin coating technique",
Applied Physics A, 2010

<1 %

Publication

49

Xiuting Luo, Ji Young Ahn, Soo Hyung Kim.
"Aerosol synthesis and luminescent
properties of CaAl₂O₄:Eu²⁺, Nd³⁺ down-
conversion phosphor particles for enhanced
light harvesting of dye-sensitized solar cells",
Solar Energy, 2019

<1 %

Publication

Exclude quotes

Off

Exclude matches

Off

Exclude bibliography

On